



Amstrong[®]

High Strength Steels with proven performance





Commitment towards net zero steel.

XCarb® brings together ArcelorMittal's reduced and low carbon-emissions products and steelmaking activities, as well as wider initiatives and green innovation projects, into a single effort focused on achieving demonstrable progress towards net-zero steel.

XCarb® recycled and renewably produced steel is applied to steels produced in an electric arc furnace (EAF) using high levels of scrap and 100-percent renewable electricity.

Our XCarb® steel certificates allow customers to reduce their or their customers's scope 3 emissions. These can be purchased directly from ArcelorMittal Europe – Flat Products in conjunction with a corresponding steel order.

More about XCarb®:

europe.arcelormittal.com/xcarb

At ArcelorMittal, we are committed to providing steel solutions that enable our clients to achieve their most ambitious objectives. **Amstrong® High Strength and Ultra High Strength Steels** embody this dedication, delivering outstanding performance and reliability for even the most demanding applications.

Developed through a process of continuous innovation and close collaboration, these materials offer the strength and durability needed to support progress across a range of industries. Choosing Armstrong® steels means gaining access to high-performance materials designed for adaptability and excellence in today's competitive landscape.

Amstrong®

The Armstrong® and Armstrong® Ultra series are available as thermomechanically rolled coils, slit coils and cut-to-length sheets. Their main properties include high yield strength and tensile strength, combined with excellent formability, weldability, toughness at low temperatures and fatigue resistance.


These grades are therefore an excellent choice for reducing structural thickness and weight whilst improving load-bearing capacity, thereby reducing the CO₂ footprint and generating cost savings and securing market advantage.




Amstrong®

Amstrong® High Strength Steels can be used with considerable advantage in a wide range of applications, including:

- Truck trailers and tippers
- Container construction
- Truck-mounted cranes and construction cranes
- Excavators and construction vehicles
- Agricultural vehicles and machinery
- Concrete mixers and pumps
- Freight and passenger rail cars
- Light poles
- Safety barriers
- Racks, shelving and many more...





Chemistry and mechanical properties

The Armstrong® and Armstrong® Ultra product ranges are manufactured according to very strict production processes, which make it possible to provide an outstanding range of properties. These grades also have better ductility and bendability than standard High Strength Low Alloy (HSLA) grades. They are therefore perfect for demanding processes, allowing trouble-free operations and ensuring constant properties from one batch of material to the next. This results in a better yield on the production line and helps to achieve the most severe tolerances on the finished steel parts. With low phosphorus (P) and silicon (Si) content, the chemical composition of these grades makes them suitable for hot-dip galvanising. Armstrong® grades fully meet or exceed all the requirements of EN 10149-2 for equivalent grades. Compared to the requirements of the EN 10149-2 standard, all Armstrong® grades come with a toughness guarantee of 40 J minimum at -20 °C ⁽¹⁾ and mechanical properties guaranteed in the rolling and transverse directions.

A 'Tough' version, with a guarantee of 27 J minimum at -40 °C ⁽¹⁾, is available for grades Armstrong® 355MC/420MC/460MC/500MC/550MC, called Armstrong® 355MCT/420MCT/460MCT/500MCT/550MCT respectively.

'Tough' versions of other grades can also be provided on request.

For higher grades ranging from minimum guaranteed yield strength 650 to 1100 MPa, please check out the Armstrong® Ultra brochure.

(1) Guarantees in the rolling direction, for standard 10 x 10 mm Charpy samples – for low thicknesses, subsize test samples are used and required values are decreased proportionally.

Chemical composition

Armstrong®	C (%)	Mn (%)	P (%)	S (%)	Si (%)	Al (%)	Nb (%)	V (%)	Ti (%)	Mo (%)	B (%)	C _{eq} (CEV)	Galvanisability
240MC	≤ 0.100	≤ 0.80	≤ 0.020	≤ 0.020	≤ 0.03	≥ 0.015	≤ 0.025	≤ 0.200	≤ 0.150	-	-	≤ 0.18	Cat A/Class 1
280MC	≤ 0.080	≤ 0.80	≤ 0.020	≤ 0.015	≤ 0.03	≥ 0.015	≤ 0.025	≤ 0.200	≤ 0.150	-	-	≤ 0.23	Cat A/Class 1
315MC	≤ 0.100	≤ 0.70	≤ 0.020	≤ 0.015	≤ 0.03	≥ 0.015	≤ 0.045	≤ 0.200	≤ 0.150	-	-	≤ 0.25	Cat A/Class 1
355MC	≤ 0.100	≤ 1.40	≤ 0.020	≤ 0.015	≤ 0.03	≥ 0.015	≤ 0.065	≤ 0.200	≤ 0.150	-	-	≤ 0.32	Cat A/Class 1
390MC	≤ 0.100	≤ 1.50	≤ 0.020	≤ 0.012	≤ 0.03	≥ 0.015	≤ 0.065	≤ 0.200	≤ 0.150	-	-	≤ 0.36	Cat A/Class 1
420MC	≤ 0.110	≤ 1.50	≤ 0.020	≤ 0.012	≤ 0.03	≥ 0.015	≤ 0.065	≤ 0.200	≤ 0.150	-	-	≤ 0.38	Cat A/Class 1
460MC	≤ 0.120	≤ 1.50	≤ 0.020	≤ 0.012	≤ 0.03	≥ 0.015	≤ 0.080	≤ 0.200	≤ 0.150	-	-	≤ 0.40	Cat A/Class 1
500MC	≤ 0.120	≤ 1.70	≤ 0.020	≤ 0.012	≤ 0.03	≥ 0.015	≤ 0.090	≤ 0.200	≤ 0.150	-	-	≤ 0.42	Cat A/Class 1
550MC	≤ 0.100	≤ 1.70	≤ 0.020	≤ 0.012	≤ 0.03	≥ 0.015	≤ 0.090	≤ 0.200	≤ 0.150	-	-	≤ 0.44	Cat A/Class 1
600MC	≤ 0.120	≤ 1.90	≤ 0.020	≤ 0.015	≤ 0.03	≥ 0.015	≤ 0.090	≤ 0.200	≤ 0.220	-	-	≤ 0.44	Cat A/Class 1

Values in **bold** are tighter than the EN 10149-2 standard
Galvanisability according to EN 10149-2 and NFA 35-503
V + Nb + Ti ≤ 0.22%

Mechanical properties

Mechanical properties									Min. impact toughness KV (J) ⁽¹⁾		
Armstrong®	Direction	R _e (MPa)	R _m (MPa)	A ₈₀ (%)		A 5.65/√S ₀ (%)	Bending ratio (th)*			at -20 °C ≥ 6	at -40 °C ≥ 6
				< 2	2-3		≥ 3	< 6	6-13		
240MC	R	240 - 320	340 - 450	≥ 27		≥ 32				≥ 40	
	T	260 - 340	340 - 450	≥ 26		≥ 31	0				
280MC	R	280 - 350	370 - 450	≥ 26		≥ 30				≥ 40	
	T	300 - 380	370 - 450	≥ 25		≥ 29	0				
315MC	R	315 - 395	415 - 495	≥ 25		≥ 28				≥ 40	
	T	340 - 420	420 - 500	≥ 23		≥ 27	0				
355MC	R	355 - 435	430 - 520	≥ 22		≥ 25				≥ 40	
	T	380 - 460	440 - 530	≥ 21		≥ 24	0				
355MCT	R	355 - 435	430 - 520	≥ 22		≥ 25				≥ 40	≥ 27
	T	380 - 460	440 - 530	≥ 21		≥ 24	0				
390MC	R	390 - 480	460 - 560	≥ 20		≥ 24				≥ 40	
	T	420 - 500	470 - 570	≥ 19		≥ 23	0				
420MC	R	420 - 520	490 - 600	≥ 18		≥ 22				≥ 40	
	T	450 - 550	500 - 600	≥ 17		≥ 21	≥ 0.2		≥ 0.5		
420MCT	R	420 - 520	490 - 600	≥ 18		≥ 22				≥ 40	≥ 27
	T	450 - 550	500 - 600	≥ 17		≥ 21	≥ 0.2		≥ 0.5		
460MC	R	460 - 560	520 - 640	≥ 15		≥ 18				≥ 40	
	T	490 - 590	530 - 640	≥ 14		≥ 17	≥ 0.6	≥ 1			
460MCT	R	460 - 560	520 - 640	≥ 15		≥ 18				≥ 40	≥ 27
	T	490 - 590	530 - 640	≥ 14		≥ 17	≥ 0.6	≥ 1			
500MC	R	500 - 600	560 - 700	≥ 15	≥ 16	≥ 19				≥ 40	
	T	530 - 630	570 - 700	≥ 14	≥ 15	≥ 18	≥ 0.6	≥ 1			
500MCT	R	500 - 600	560 - 700	≥ 15	≥ 16	≥ 19				≥ 40	≥ 27
	T	530 - 630	570 - 700	≥ 14	≥ 15	≥ 18	≥ 0.6	≥ 1			
550MC	R	550 - 650	620 - 750	≥ 12		≥ 14				≥ 40	
	T	580 - 680	630 - 750	≥ 11		≥ 13	≥ 0.8	≥ 1.5			
550MCT	R	550 - 650	620 - 750	≥ 12		≥ 14				≥ 40	≥ 27
	T	580 - 680	630 - 750	≥ 11		≥ 13	≥ 0.8	≥ 1.5			
600MC	R	≥ 600	650 - 820	≥ 11		≥ 13				≥ 40	
	T	≥ 620	660 - 820	≥ 10		≥ 12	≥ 1.5				

* Minimum mandrel diameter for 180° bend

(1) The impact energy is verified for products with a nominal thickness ≥ 6 mm as defined in the relevant EN standard. It is possible to have impact energy verified on request for nominal thickness ≥ 5 mm. Impact toughness below 5 mm is guaranteed without testing.

Dimensional feasibility

One of the most outstanding features of the Armstrong® range is its dimensional feasibility. This enables tangible production benefits such as:

- Stock optimisation for maximum flexibility
- Improved nesting/productivity of the cutting line and higher material yield
- Manufacture of larger and simpler parts, reducing the number of welds needed resulting in lower production costs.

Armstrong® and Armstrong® Ultra steel grades are available as mill finish coils or pickled and oiled. Armstrong® products are also available with improved surface finish. For the most demanding surface needs, our grades can be ordered with Micro Adhesive Scale (MASC). We're constantly improving our dimensional availability, for further information please consult us.

Feasibility mill finish coils, mill edge

MC versions		Max width (mm)															
Thickness (mm)	1.2	1.5	1.8	2	3	4	5	6	7	8	10	12	15	16	17	20	
Amstrong® 240MC	1000	1550	1640	1840	2050	2135		2050							1370		
Amstrong® 280MC		1350	1450	1600	2030	2130			2030	1880	1710	1370					
Amstrong® 315MC	985	1550		1600	1885	2135	2150							2050	1370		
Amstrong® 355MC	985	1550		1600	1830	2050	2150										
Amstrong® 390MC			1100	1250	1580	2040	2150										
Amstrong® 420MC			1350	1510	1600	2000	2150							1370			
Amstrong® 460MC		1270	1330	1510	1750	2040	2150						2051				
Amstrong® 500MC		1180	1330		1580	2020	2150				2050						
Amstrong® 550MC			1300		1600	2020	2150			1935	1550						
Amstrong® 600MC				1300	1520	1700	1900	2135		2050							
MCT versions		Max width (mm)															
Thickness (mm)	1.5	1.8	2	3	4	5	6	7	8	10	12	15	16	17			
Amstrong® 355MCT	1250	1420	1535	1790	2050	2135						2050					
Amstrong® 420MCT		1000	1270	1580	2040	2150						2050		1370			
Amstrong® 460MCT		1000	1270	1580	2040	2150											
Amstrong® 500MCT			1230	1500	2020	2150											
Amstrong® 550MCT			1230	1500	2020	2150											

Feasibility pickled and oiled – up to 15 mm on request

MC versions		Max width (mm)											
Thickness (mm)	1.2	1.5	1.8	2	3	4	5	6	8	10	12	13	
Armstrong® 240MC	1275	1550	1640	1840	2035	2110		1765	1525				
Armstrong® 280MC		1320	1470	1570	1885	1730		1590					
Armstrong® 315MC	1275	1550			1885	2110			1525				
Armstrong® 355MC	1275	1550			1740	2040	2110		1550	1525			
Armstrong® 390MC			1100	1275	1585	2040	2097		1270				
Armstrong® 420MC			1350		1510	1660	2040	2097		1525			
Armstrong® 460MC		1270	1330	1510	1587	2040	2070		1525				
Armstrong® 500MC		1180	1330	1335	1660	2020	2070		1525				
Armstrong® 550MC			1300		1608	2020	2070		1525				
Armstrong® 600MC				1300	1608	1699	1660	1525					
MCT versions		Max width (mm)											
Thickness (mm)	1.5	1.8	2	3	4	5	6	8	10				
Armstrong® 355MCT	1195	1380	1525	1740	2035	2110		1550	1525				
Armstrong® 420MCT			1000	1275	1660	2070							
Armstrong® 460MCT			1000	1270	1580	2070							
Armstrong® 500MCT				1230	1500	2070							
Armstrong® 550MCT				1230	1500	2070							

Processing

Armstrong® and Armstrong® Ultra products have a low carbon equivalent value and can therefore be easily welded using various welding techniques. When required as sheets, they can be supplied with tight flatness tolerance thanks to the use of selected cut-to-length lines. They are therefore perfectly suited for oxy-fuel, plasma or laser cutting. Laser-cutting ability is also improved thanks to the low carbon and silicon content. For further information please contact us prior to order.

Availability

Armstrong® and Armstrong® Ultra products are manufactured in several European ArcelorMittal steel mills, which means that you will always have easy access to them wherever you are located. They can also be found in stock at various Steel Service Centres.

Since ArcelorMittal operates a policy of continuous development, our product range and dimensional feasibility is naturally constantly changing. We therefore advise you to regularly check the dedicated leaflet and product data sheets A20 and A22 in our online product catalogue at industry.arcelormittal.com/catalogue – remember that stock sizes vary over time.

Innovative High Strength Steels for sustainability

ArcelorMittal's High Strength Low Alloy grades, such as Armstrong® 500MC and Armstrong® Ultra 700MC, offer exceptional weight-saving benefits, thanks to thinner, stronger steel that is easier to weld. These advanced materials translate into lower material costs, fuel savings, and significant CO₂ reductions over a product's lifetime.

The use of thinner High Strength Low Alloy steels provides several advantages. It enables faster cutting, forming, and welding processes due to less material and lower energy requirements, resulting in increased productivity and reduced costs. Thinner sheets also enhance precision, are easier to handle and transport, and allow for more complex designs.

Using XCarb® recycled and renewably produced Armstrong® for construction and mining machinery results in a 75% lower carbon footprint compared with traditional manufacturing.

Develop your product with us.



Trailer chassis

Armstrong® Ultra 700MC and Armstrong® 500MC enable **39% weight reduction** and **38% CO₂ savings** during material production compared to structural steel. We provide full support, from design through welding, ensuring optimised fatigue performance for your trailer chassis.



Tipper

Entire body composed of Armstrong® Ultra 700MC and Armstrong® 420MC structural components, **20% weight** and **CO₂ reduction** compared with structural steel grades. T-bone hook replaced with Armstrong® 500MC, **35% weight reduction** and **25% cost saving**.



Racking system

Armstrong® and Armstrong® Ultra products are a perfect alternative to standard structural steel grades to create **low maintenance** racking systems which are very **cost effective** over their entire lifetime.



Trailer part made of 12 mm Armstrong® Ultra 700MC, laser cut and bent.

Case study

Trailer material optimisation with Armstrong® and Armstrong® Ultra steels

A trailer chassis built using Armstrong® 500MC and Armstrong® Ultra 700MC achieves:

- **29% material cost reduction** compared to traditional structural steel.
- **700 litres of fuel savings annually**, assuming an average of 150,000 km driven per year.
- **900 kg CO₂ emissions reduction** each year, thanks to lightweight materials and fuel efficiency.
- **0.4–0.6 litres per 100 kilometres** of fuel savings can be achieved.

By utilising these innovative high-strength steels, our customers gain a competitive edge while supporting their sustainability goals.

For more information about Armstrong® steels: armstrong.arcelormittal.com

Credits

Shutterstock.com – Parilov, Jeroen Op de Beeck & donvictorio@o2.pl, Mark William Richardson, Jarp2, Christian Lagerek, Stephen Aaron Rees, Niels Quist, Don Donelson, Viktor1, Bailey Image, David Lade, Dmitry Kalinovsky, ETIENjones, Petinov Sergey Mihilovich / Shutterstock.com

Copyright

All rights reserved for all countries. This publication shall not be reproduced, in whole or in part, in any form or by any means whatsoever, without prior express written consent from ArcelorMittal. Care has been taken to ensure that the information in this publication is accurate, but this information is not contractually binding. ArcelorMittal and any other ArcelorMittal Group company do not therefore accept any liability for errors or omissions or any information that is found to be misleading. As this document may be subject to change at any time, please consult the latest information in the product document centre at industry.arcelormittal.com

